
Heat Seal Tea Bag Filter Paper in roll



Heat Seal Tea Bag Filter Paper in roll



Place of Origin:Guangdong, China

Material:Wood Pulp

Usage:packaging, medical

Thickness:54um-72um

Grammage: 16.5gsm, 17gsm, 18gsm, 20gsm, 21gsm, 22gsm, 23gsm, 25gsm

Color:according to customer`s request

Film width: according to clients request

Available width: 87mm, 125mm, 130mm, 140mm, 264mm, 320mm, 370mm, 484mm, 564mm

It can be widely used in the latest packing machines


ITALY IMA (C2000, C51, CA1, CA3, CAL123)

Argentina MAIS.A (EC12, EC12/B, EC12/C-Y)

Germany tee pack CONSTANTA, etc.

It's available for all of Chinese DXD, YD tea bag packing machines.





Available width: 87mm,125mm,130mm,140mm,264mm,320mm,370mm,484mm,564mm



热封型茶叶滤纸产品标准

Heatseal Tea/coffee bag Filter Paper Product Standards

名称 Product Name		热封型茶叶/咖啡滤纸 Heatseal Tea/coffee bag Filter Paper							
参数 Parameter	单位 Unit	数值 Value							标准 Test method
定量 Substance	g/m ²	16.5± 1. 0	18.0± 1. 0	21.0± 1. 0	23.0± 1. 0 (21gB)	25.0±1. 0	30.0± 1.0	25.0± 1.2 (abaca)	GB/T 451.2
干纵向≥ Tensile strength dry MD	Kn/ m	0.60	0.65	0.80	0.85	0.90	1.20	1.50	GB/T 453
干横向≥ Tensile strength dry CD	Kn/ m	0.14	0.16	0.20	0.20	0.21	0.23	0.30	GB/T 453
湿纵向≥ Tensile strength wet MD	Kn/ m	0.18	0.20	0.22	0.23	0.24	0.25	0.40	GB/T 465.2
湿横向≥ Tensile strength wet CD	Kn/ m	0.08	0.10	0.12	0.12	0.12	0.13	0.14	GB/T 465.2
水分 Moisture	%	7.0± 2. 0	7.0± 2. 0	7.0± 2. 0	7.0±2. 0	7.0±2. 0	7.0±2. 0	7.0± 2. 0	GB/T 462
白度 Brightness	%	>75.0	>75.0	>75.0	>75.0	>75.0	>75.0	>75.0	GB/T 7974
用途 Use		茶叶包 装 Tea Packagi ng	茶叶包 装 Tea packagi ng	茶叶调 味料中 药包装 Tea, Seasoni ng , Traditio nal Chinese medicin e packagi ng	茶 叶 、 咖 啡 ， 调 味 料、中药包 装 Tea, coffee, Seasoning , Traditional Chinese medicine packaging	咖 啡 包 装 滤 纸 Coffer filter paper packaging	茶 叶 包 装 Tea packagin g	咖 啡 包 装滤纸 Coffer filter paper packagi ng	

Product link : <https://www.oempackagingbag.com/heat-seal-tea-bag-filter-paper-in-roll.html>